

Packstat PS080 is primarily a foam compression sealant. The product is grey. The foam is predominantly closed celled and is a hard foam. An acrylic pressure sensitive adhesive is coated on one side, and the product has a paper release liner on the other non-adhesive face. PS080 will act as a water-seal and air/dust seal when compressed.

Product Benefits

- Minimum 30% compression required to affect a water seal.
- Service temperature: -30°C to +70°C.
- Application temperature: +10°C to +40°C.
- Shelf life of 1 year from date of dispatch.
- Coated on one side with a high-quality pressure sensitive acrylic adhesive
- Good resistance to dilute acids and alkalis.
- Paper release liner on the non-adhesive face, reducing dimensional change during application.
- Very good ultraviolet {UV} light resistance.
- Resistance to abrasion, corrosion and moisture
- Suitable for indoor and outdoor environments
- No known hazards associated with this product.
- Pre-determined dimensional sealant reduces waste.
- Clean to use / clean edge finish.

Main Applications

- Forms a compression water seal.
- For preventing electrolytic corrosion
- For heavy duty cushioning.
- Forms a compression air / dust seal.
- For gap filling.
- For high load bearing applications

Product Properties	Unit	Nominal Value
10 Minute 180° Peel Adhesion	N/25mm	5
Force to Compress by 30%	N/cm ²	6.1
Compression Deflection After 1 Minute	N/cm ²	5
Foam Density	Kg/mg ³	220
Shore Hardness {00} Scale	"00"	50
Elongation at Break	%	>180
Tensile Strength	N/cm ²	66
Thermal Conductivity (k)	Wm ⁻¹ K-	0.043

Accreditation:

Conforms to European Directive 2000/53 EC (lead, chromium VI, mercury, cadmium free).

Fire rated to DIN 4102 part 1, B2.

Conforms to AbP DIN EN 13501-1: 2010 Class E.

Recommendations:

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and +30°C. Under these conditions, the shelf life of the tape is 12 months from the date of dispatch.

Surfaces should be clean, dry and free of dust, grease, oil or other contaminants. Customers are recommended to make their own assessment of our products under their own conditions, for their own requirements.